

## OK Tigrod 12.64

A copper coated, G4Si1/ER70S-6 rod for GTAW of general structural and engineering unalloyed and low-alloyed carbon-manganese steels. Compared with OK Tigrod 12.61, OK Tigrod 12.64 has a slightly higher silicon and manganese content, which increases the weld metal strength. The high silicon content promotes low sensitivity to surface impurities and contributes to smooth, sound welds.

Specifications	
<b>Classifications</b>	EN ISO 636-A : W 46 5 4Si1 EN ISO 636-A : W 4Si1 SFA/AWS A5.18 : ER70S-6
<b>Approvals</b>	ABS : 3Y (I1) BV : 3YM CE : EN 13479 DNV-GL : III YM (I1) LR : 3Ym H15 (I1) NAKS/HAKC : 1.6MM-2.4MM VdTÜV : 05260

<b>Alloy Type</b>	Carbon-manganese steel
-------------------	------------------------

Typical Tensile Properties			
Condition	Yield Strength	Tensile Strength	Elongation
<b>Ar (I1) AWS</b>			
Stress Relieved 2 hour(s) 620 °C	400 MPa	525 MPa	32 %
As Welded	510 MPa	610 MPa	30 %
<b>Ar (I1) EN</b>			
As Welded	525 MPa	595 MPa	26 %

Typical Charpy V-Notch Properties		
Condition	Testing Temperature	Impact Value
<b>Ar (I1) AWS</b>		
Stress Relieved 2 hour(s) 620 °C	-46 °C	80 J
As Welded	-46 °C	100 J
<b>Ar (I1) EN</b>		
As Welded	-50 °C	90 J
As Welded	-40 °C	150 J

Typical Weld Metal Analysis %				
C	Mn	Si	S	P
<b>Ar</b>				
0.08	1.28	0.80	0.013	0.015

Typical Wire Composition %		
C	Mn	Si
0.074	1.68	0.95